

	750	1000	1200
Nominal Weight	7.5 osy (255gsm)	10.0 osy (340gsm)	12.0 osy (410gsm)
Woven Type	Twill	Twill	Twill
Colors	Chambray & Cool Blue	Navy Blue	Navy Blue
Made in America	Yes		
Electric Arc Rating NFPA 2112	6.5 cal/cm ²	8.2 cal/cm ²	9.0 cal/cm ²
Vertical Flammability	ASTM D 6413-99		
char length after flame	<5.0 in (12.7cm) <2.0 sec	<5.0 in (12.7cm) <2.0 sec	<5.0 in (12.7cm) <2.0 sec
Molten Metal Splash Resistance	ISO 11612		
molten ai splash molten fe splash	level D2 level E3	level D3 level E3	level D3 level E3
Arc Thermal Performance Value (ATPV) ASTM F 1959	6.5 cal/cm ²	7.0 cal/cm ²	7.0 cal/cm ²
Dimensional Stability	120°F Permanent Press Cycle Tumble Dry Low AATCC 135		
after 5 launderings	<5.0 in	<5.0 in	<5.0 in
Pilling Resistance	ASTM O3512. Ratings 5 Best, 3 Acceptable, 1 Poor		
30 minutes	5	5	5
60 minutes	4 - 5	5	4
90 minutes	4	4	5
120 minutes	4	4	4
Crocking	AATCC 8 Ratings 5 Best, 3 Acceptable, 1 Poor		
wet	4	4 - 5	4
dry	5	5	4 - 5
SunSHIELD™ UV Protection AATCC 16 Ratings 5 Best, 3 Acceptable, 1 Poor	4 - 5	4 - 5	4 - 5